Power Grab[®] Ultimate Construction Adhesive

DESCRIPTION

Power Grab[®] Ultimate Construction Adhesive is an interior/exterior construction adhesive with Zero Second Instant Grab[®] which bonds to many porous and non-porous materials. This formula works in all conditions, all weather and delivers excellent results in many applications.

Available as:

Item #	Package	Size	Color
2999434	Plastic cartridge	9 fl. oz. (266 mL)	White

FEATURES & BENEFITS

- Zero Second Instant Grab^{® [1]}
- Long lasting adhesion to a variety of substrates
- Suitable for interior and exterior use

RECOMMENDED FOR

Bonds to most common construction materials such as wood, drywall, plaster, ceramic, porcelain, concrete, masonry, brick, granite, most metals and stone ^[2], foam insulation (EPS and XPS), fiberglass, some plastics and more.

LIMITATIONS

- · Marine and water submersion applications or constantly damp environments
- Polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE), flexible/plasticized vinyl (FPVC), acrylic glass, copper, brass or bronze surfaces
- Areas of high heat, such as fireplace openings
- Certain natural stones ^[2] such as limestone, travertine, or sandstone
- Bituminous coated surfaces or materials
- Certain materials such as rubbers and plastics may have bonding difficulties. Test before use.
- Mirrors
- Flexible sheet goods

COVERAGE

For a 9 fl. oz. (266 mL) cartridge:

• A 1/4" (6 mm) bead extrudes approximately 28 lin. ft. (8.5 m) • A 3/8" (9.5 mm) bead extrudes approximately 12.3 ft. (3.7 m)

Typical Uncured Physical Properties		Typical Application Properties			
<u>Color:</u>	White		Application Temperature:	Apply and cure above 40°F (5°C)	
Appearance:	Thick paste			and below 105°F (40°C)	
Base:	Silane Modified Poly	ymer	<u>Odor:</u>	Alcohol	
Viscosity:	300,000 - 700,000	cPs	<u>Open Time:</u>	10 – 15 minutes*	
VOC Content:	2.88% by weight	CARB	Repositioning Time:	5 – 10 minutes*	
	46.94 g/l	SCAQMD	Clamping Time:	24 hours	

¹ Under normal conditions holding in place for about 30 seconds or more should be sufficient. However, depending upon the weight of the object being bonded and vertical load conditions temporary blocking may be required until adhesive is fully cured.

² Some natural stone materials may have unpredictable surface characteristics. Therefore, we recommend testing for adhesion by applying adhesive to a small area before proceeding with an entire job.



Technical Data Sheet

TECHNICAL DATA						
Typical Uncured Physical Properties		Typical Application Properties				
Shelf Life:	18 months from date of manufacture	Cure Time:	24 – 48 hours*			
Shell Life. 18 months from date of manufacture (unopened) Lot Code Explanation: YYDDD YY = Last two digits of year of manufacture DDD = Day of manufacture based on 365 days in a year Example: 22248 = 248th day of 2022 = September 5, 2022		<u>Clean up:</u>	Clean up uncured adhesive residue with mineral spirits. Cut or scrape away cured adhesive using a sharp-edged tool. Note this may result in damage to surfaces. Follow solvent manufacturer's precautions for using solvents.			

* At 73°F (23°C) and 50% relative humidity

Time is dependent on temperature, humidity, porosity of substrate, and amount of adhesive applied

Typical Cured Performance Properties					
Color:	White	Service Temperature:	-22°F (-30°C) to 158°F (70°C)		
Cured form:	Non-flammable, hard solid	Water Resistance:	Yes		
Paintable:	Yes, with water-based acrylic paint				
Shear Strength,	ASTM D3498:				
Dry Lumber	225 psi				
Wet Lumber	115 psi				
Frozen Lumbe	r 135 psi				

DIRECTIONS

Tools Typically Required:

Utility knife, caulking gun, plant mister bottle containing water (if bonding two non-porous surfaces).

Safety Precautions:

Moisture resistance

Wear gloves to avoid skin contact and wash hands after use.

184 psi

183 psi

Preparation:

Gap Filling

The temperature of the bonding surfaces and working area must be between $40^{\circ}F$ ($5^{\circ}C$) and $105^{\circ}F$ ($40^{\circ}C$). For best results and smooth, fast, easy application during cold weather, store adhesive at room temperature ($70^{\circ} \pm 5^{\circ}F$) 24 hours prior to use and ensure product temperature is $60^{\circ}F$ ($15^{\circ}C$) or higher but below $90^{\circ}F$ ($32^{\circ}C$). Ensure surfaces to be bonded are clean, structurally sound, and free of standing water, dust, grease, oil, and/or other contaminants. Pre-fit all materials prior to applying product and protect finished surfaces. Remove nozzle and cut nub. Screw on nozzle and cut at a 45° angle to required opening size, at least ¼ inch or wider. Be very careful not to allow LOCTITE Power Grab Ultimate to cure on a finished surface (removal may not be possible without surface damage).

NOTE: Do not use on building materials that are warped or show evidence of warping. These materials will experience bonding difficulties.

General Application:

Apply adhesive to one of the bonding surfaces. Press surfaces firmly together within 10 - 15 minutes. If necessary, materials may be repositioned within ~5 minutes of pressing surfaces together. If bonding two non-porous surfaces or under very dry conditions (less than 30% relative humidity), add water in the form of a very light or atomized spray from a plant mister bottle to the extruded adhesive. The repositioning time will then be reduced to less than 5 minutes. Use mechanical support or temporary bracing for 24 - 48 hours, depending upon project requirements, while the adhesive cures. Cure time is dependent upon temperature, humidity, porosity of substrate and amount of adhesive used. Low temperature and humidity will slow cure time. When bonding EPS and XPS foam insulation, avoid cure and surface temperatures above $90^{\circ}F$ ($32^{\circ}C$) as this may cause cavitation of the foam.

NOTE: User is responsible for determining suitable and acceptable results for their intended project. Test before use



Technical Data Sheet

DIRECTIONS

Application Tips:

- 1. For small, relatively smooth and level surfaces use straight, parallel beads of adhesive (Fig.1)
- 2. For large areas parallel serpentine beads may work best, placed 6 8" O.C. (Fig. 2)
- **Note:** In case of two non-porous surfaces, adhesive beads must not merge or form a continuous area as air/moisture contact with applied adhesive is required for proper cure.
- 3. When using for exterior/outdoor applications, it is best to apply vertical beads of adhesive (from top to bottom) to help support vertical load conditions.
- 4. For rough and uneven surfaces using the spot/dollop method may work best (Fig. 3)



Clean-up:

Clean tools and uncured adhesive residue immediately with mineral spirits in a well-ventilated area to the outdoors. Follow solvent manufacturer's precautions for using solvents. Cured adhesive may be carefully cut or scraped away with a sharp-edged tool. Note this may result in damage to surfaces.

STORAGE & DISPOSAL

NOT DAMAGED BY FREEZING. For best results store unopened product at standard conditions which are defined as $72 \pm 4^{\circ}$ F ($22 \pm 2^{\circ}$ C) and < 50% relative humidity. Use an approved hazardous waste facility for disposal, and in accordance with local and federal regulations.

LABEL PRECAUTIONS

WARNING! UNCURED ADHESIVE IRRITATES EYES, SKIN, AND RESPIRATORY TRACT

Warning! Contains crystalline silica and silanes. May be harmful if inhaled or swallowed. Methanol is released during application and cure, which may affect the nervous system causing dizziness, headache, or nausea. Use in a well-ventilated area. Do not breathe vapors. Avoid eye and skin contact. Prolonged or repeated skin contact with uncured adhesive may cause irritation. Wear gloves and safety glasses when applying product. Remove contact lenses before using adhesive. Wash hands after using.

FIRST AID: For eye contact flush with water for 15 minutes. Call a physician if irritation develops and persists. For skin contact, wash thoroughly with soap and water. If affected by inhalation, remove to fresh air and get medical attention. If ingested, do not induce vomiting; call a physician or Poison Control Center immediately. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

WARNING: Risk of Cancer and Reproductive Harm – <u>www.P65Warnings.ca.gov</u>

Refer to the Safety Data Sheet (SDS) for further information.

DISCLAIMER

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Henkel recommends purchasers/users should test the products to determine acceptable quality and suitability for the intended use. All adhesive/sealant applications should be tested under simulated or actual end use conditions to ensure the adhesive/sealant meets or exceeds all required project specifications. Since assembly conditions may be critical to adhesive/sealant performance, it is also recommended that testing be performed on specimens assembled under simulated or actual production conditions. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.



Technical Data Sheet

LIMITED WARRANTY

This product is warranted by Henkel Corporation to be free from defects in materials when used as directed. Henkel's sole obligation shall be, at its option, to replace or refund the purchase price of product proven to be defective. Henkel makes no other warranty – express or implied – including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE and will not be liable for consequential or incidental damages. For warranty assistance, contact Henkel at 1.800.624.7767 M-F 9:00 am to 4:00 pm ET.

